




Duplex/Super Duplex Pipe/Tube

Manufacturer of austenitic, duplex and nickel alloy welded/seamless stainless steel pipes/tubes

www.eb-stainless.com



Material Available:

UNS S32001, S31500, S32304, S31803, S32205, S32760, S32750

Standard: ASTM A/SA 789/M

Seamless Ferritic and Austenitic Stainless Steel Tubing for General Service

ASTM A/SA 790/M

Seamless and Welded Ferritic/Austenitic Stainless Steel Pipe

ASTM A/SA 928/M

Ferritic/Austenitic (Duplex) Stainless Steel Pipe Electric Fusion Welded with Addition of Filler Metal

Mechanical Properties

Steel grade	Tensile strength, MPa	Percent elongation, % (Not less than)
S32001	620	25
S31500	630	30
S32304	OD 1 in. (25 mm) and Over	690
	OD over 1 in. (25 mm)	600
S31803	620	25
S32205	655	25
S32760	750	25
S32750	800	15

Chemical composition Limits, %^a

Steel Grade ^b	C	Mn	Si	P	S	Cr	Ni	Mo	N	Cu	Others
S32001	0.03	4.00-6.00	1.00	0.040	0.030	19.5-31.5	1.0-3.0	0.60	0.05-0.17	1.00	
S31500	0.03	1.20-2.00	1.40-2.00	0.030	0.030	18.0-19.0	4.3-5.2	2.50-3.00	0.05-0.16	-	
S32304	0.03	2.50	1.00	0.040	0.040	21.5-24.5	3.0-5.5	0.05-0	0.05-0.20	0.05-0.6	
S31803	0.03	2.00	1.00	0.030	0.020	21.0-23.0	4.5-6.5	2.5-3.5	0.08-0.20	*	
S32205	0.03	2.00	1.00	0.030	0.020	22.5-23.0	4.5-6.5	3.0-3.5	0.14-0.20	*	
S32760	0.05	1.00	1.00	0.030	0.010	24.0-26.0	6.0-8.0	3.0-4.0	0.20-0.30	0.5-1.0	c
S32750	0.03	1.20	0.80	0.035	0.020	24.0-26.0	6.0-8.0	3.0-5.0	0.24-0.32	0.50	

a: weight percent, maximum unless otherwise noted.

b: new designation established in accordance with Practice E527 and SAE J1086

c: w: 0.50-1.00; cr+3.3mo+16n=40 min.

Size Available

	Standard	Outside diameter		Wall thickness		Tolerances on
		mm	inch	mm	inch	
Seamless pipe/tube	ASTM A/SA 789/M	12.7-203.2	0.5"-8"	0.5-6.35	0.0197"-0.250"	Please refer to relative Standard
	ASTM A/SA 790/M	10.3-273	0.405"-10.75"	0.5-16.0	0.0197"-0.630"	
Welded pipe/tube	ASTM A/SA 789/M	12.7-203.2	0.5"-8"	0.5-4.0	0.0197"-0.157"	
	ASTM A/SA 790/M	10.3-406.4	0.405"-16"	0.5-10.0	0.0197"-0.394"	
	ASTM A/SA 928/M	10.3-406.4	0.405"-16"	0.5-10.0	0.0197"-0.394"	

Notes:

1. Tubes will pass tensile test, flaring test, flange test, reverse flattening test and non-destructive test, they shall be tested for hardness and grain size
2. Upon request tubes shall be submitted to intergranular corrosion test
3. Tubes of other dimensions and lengths can be manufactured upon agreement within the customer and us

Seamless pipes/tubes are in lengths of MAX. 15 meter.
Welded pipes/tubes are in lengths of MAX. 22 meter.

APPLICATIONS

- Heat exchangers, tubes and pipes for production and handling of gas and oil,
- Heat exchangers and pipes in desalination plants,
- Pressure vessels, pipes, tanks and heat exchangers for processing and transport of various chemicals,
- Pressure vessels, tanks and pipes in process industries handling solutions containing chlorides,
- Rotors, fans, shafts and press rolls where the high corrosion fatigue strength can be utilized
- Cargo tanks, piping and welding consumables for chemical tankers.

B-602, Zhongxin Plaza, HuZhou, ZheJiang, China, 313000

Tel: +86 (0)572 2033 388 Fax: +86 (0)572 2033 602

Email: info@eb-stainless.com